



(19)

Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 111 097 A2



(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

27.06.2001 Bulletin 2001/26

(51) Int Cl.7: **C25D 3/60, C25D 3/58**

(21) Application number: **00309301.0**

(22) Date of filing: **23.10.2000**

(84) Designated Contracting States:

**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**

Designated Extension States:

AL LT LV MK RO SI

(72) Inventor: **Tamura, Takaaki**

Kanagawa-ku, Yokohama, Kanagawa (JP)

(74) Representative: **Jenkins, Peter David et al**

PAGE WHITE & FARRER

54 Doughty Street

London WC1N 2LS (GB)

(30) Priority: **22.12.1999 JP 36540599**

(71) Applicant: **Nippon MacDermid Co., Ltd.**

Yokohama-Shi, Kanagawa-Ken 227 (JP)

(54) **Bright tin-copper alloy electroplating solution**

(57) A tin/copper alloy electroplating solution capable of forming a bright plating film in a wide electric current density range is provided. The electroplating solu-

tion is a cyanide-free aqueous solution containing an organosulfonic acid, divalent tin and copper salts, as metal salts, of the organosulfonic acid, a dispersant, and a brightener.

EP 1 111 097 A2

Best Available Copy

Description

[0001] The present invention relates to a bright tin/copper alloy electroplating solution.

[0002] The pollution of soil and subterranean water has recently become an issue, which pollution is caused by acid-rain elution of lead from tin/lead alloy used in waste home electronic and electric appliances. This is because tin/lead alloy is widely used in mounting electronic components. Therefore, the development of a mounting solder alloy or solder plating not containing lead is keenly desired. As a plating method not giving rise to such a problem, tin/lead alloy plating is now considered promising. The tin/lead alloy plating has heretofore been used for decoration and the eutectic point of the same alloy is 227°C. Copper is less expensive than silver and bismuth the use of which is also under study at present. For example, in JP 8-27590A and JP 8-27591A there are disclosed bright tin/copper alloy plating solutions as copper alloy plating solutions. But these plating solutions involve a serious problem that they contain a cyanide and an alkali cyanide as essential components. Also, in JP 5.7-60092A, JP 57-101687A, JP 58-9839A, JP 58-91181A, JP 59-4518A, JP 60-12435A, and JP 4-13434A there are disclosed tin/copper plating solutions. With these tin/copper plating solutions, however, a bright plating film cannot be formed in a sufficiently wide electric current density range, thus involving the problem that the electric current density range capable of affording a bright plating film is narrow or a rough and matt film is apt to be deposited at a high electric current density. Thus, it is difficult to manufacture such tin/copper plating solutions on an industrial scale.

[0003] It is a principal object of the present invention to provide a cyanide-free tin/copper alloy plating solution capable of forming a tin/copper alloy plating film superior in smoothness and brightness in a wide electric current density range and capable of being put to practical use industrially.

[0004] Having made earnest studies, the present inventors found out that a good bright electrodeposition film could be obtained in a wide electric current density range by adding a dispersant and a brightener to an aqueous solution containing an organosulfonic acid, a divalent tin salt of the organosulfonic acid, and a divalent copper salt of the organosulfonic acid. On the basis of this finding we accomplished the present invention.

[0005] The present invention resides in a cyanide-free bright tin/copper alloy electroplating solution which comprises an aqueous solution containing an organosulfonic acid, a divalent tin salt of the organosulfonic acid, a divalent copper salt of the organosulfonic acid, a dispersant, and a brightener.

[0006] The present invention, in a preferred embodiment thereof, resides in the above bright tin/copper alloy electroplating solution wherein the dispersant comprises at least two members selected from the group consisting of polyoxyethylene alkyl phenyl ethers, polyoxyethylene alkyl ethers, and alkylene glycol alkyl ethers.

[0007] The present invention, in a further preferred embodiment thereof, resides in the above bright tin/copper alloy electroplating solution wherein the brightener comprises at least two members selected from the group consisting of aliphatic and aromatic aldehydes, aliphatic and aromatic ketones, and aliphatic carboxylic acids.

[0008] The present invention, in a still further preferred embodiment thereof, resides in the above bright tin/copper alloy electroplating solution further containing an antioxidant.

[0009] The bright tin/copper alloy electroplating solution of the present invention will be described in detail hereinafter.

[0010] The organosulfonic acid used as the first essential component in the plating solution of the present invention can be represented by the following general formula (1) :



where R_1 stands for an alkyl or aryl group. In the general formula (1), the alkyl or aryl group as substituent R_1 preferably has 1 to 10 carbon atoms. Preferred examples of the organosulfonic acid are such alkanesulfonic acids as methanesulfonic acid, ethanesulfonic acid, propanesulfonic acid, 2-propanesulfonic acid, butanesulfonic acid, 2-buthanesulfonic acid, pentanesulfonic acid, hexanesulfonic acid, and decanesulfonic acid, as well as such aromatic sulfonic acids as benzenesulfonic acid, toluenesulfonic acid, xylenesulfonic acid, and phenolsulfonic acid. One or more of the organosulfonic acids thus exemplified may be used in the plating solution of the present invention. But those with R_1 in the general formula (1) being alkyl are more preferable. These acids impart an electric conductivity to the plating solution and accelerate the dissolution of tin and copper salts into the plating solution or the dissolution of a plating anode into the plating solution.

[0011] The metal salts used as the second essential component in the plating solution of the present invention are a divalent tin salt of the organosulfonic acid and a divalent copper salt of the organosulfonic acid. These salts can each be prepared easily by reacting a divalent tin or copper salt or oxide with a desired organosulfonic acid. As the substances to be reacted with the organosulfonic acid, oxides of divalent tin and copper are preferred because they are effective in preventing an anionic pollution of the resulting metal salts. The metal salts added into the plating solution serve as

a source of metal ions deposited on cathode. Tin is apt to be oxidized from divalent to tetravalent tin, so for the purpose of preventing this oxidation, such an antioxidant as catechol, resorcin, or hydroquinone, may be added into the plating solution.

[0012] The dispersant used as the third essential component in the plating solution of the present invention is not specially limited if only it is dissolved in the above basic solution. Particularly preferred are polyoxyethylene alkyl phenyl ethers, polyoxyethylene alkyl ethers, and alkylene glycol alkyl ethers. These compounds may be used each alone or in combination of two or more. Particularly, using two or more of them is preferred. As preferred examples are mentioned polyoxyethylene octyl phenyl ether, polyoxyethylene nonyl phenyl ether, polyoxyethylene dodecyl ether, polyoxyethylene alkyl ($C_{12}\sim C_{16}$) ether, propylene glycol methyl ether, dipropylene glycol methyl ether, and propylene glycol phenyl ether.

[0013] The dispersant not only functions to make a brightener easy to dissolve in the plating solution which brightener is difficult to dissolve in water, but also functions to lower the surface tension of the plating solution and thereby smooth the plating film surface and brighten its appearance. The amount of the dispersant to be used is usually in the range of 0.5 to 50 g/L, preferably 1 to 30 g/L, as a total concentration of one or more of those exemplified above in the plating solution.

[0014] As examples of the brightener used as the fourth essential component in the plating solution of the present invention, mention may be made of formaldehyde, acetaldehyde, paraldehyde, butylaldehyde, isobutylaldehyde, propionaldehyde, glyoxal, aldol, caproic aldehyde, benzaldehyde, veratraldehyde, anisaldehyde, salicylaldehyde, 1-naphthaldehyde, 2-naphthaldehyde, naphthalaldehyde, acetylacetone, benzylideneacetone, benzylideneacetylacetone, acetophenone, benzalacetone, acrylic acid, and methacrylic acid. These brighteners may each be used alone, but are preferably employed as a mixture of two or more. The concentration of the brightener in the plating solution is usually in the range of 0.01 to 20 g/L, preferably 0.1 to 10 g/L.

[0015] Into the plating solution of the present invention there may be added, for example, catechol, resorcin, hydroquinone, or pyrocatechol, as an antioxidant for suppressing the oxidation of tin. The concentration of the antioxidant in the plating solution is usually in the range of 0.1 to 20 g/L, preferably 0.2 to 10 g/L.

[0016] As plating work conditions using the bright tin/copper alloy electroplating solution of the invention, an appropriate electric current density is in the range of 0.5 to 20 A/dm² and an appropriate solution temperature is in the range of 10° to 30°C. In such a wide electric current density range it is possible to form a tin/copper alloy plating film having a good gloss and it becomes possible to carry out the plating work at a higher electric current density than in the prior art. This point, coupled with the point that the plating solution does not contain any cyanide, contributes to the improvement of the working efficiency.

[0017] According to the cyanide-free bright tin/copper alloy electroplating solution of the invention, a tin/copper alloy plating film having gloss and superior in both smoothness and macrothrowing power can be formed in a wide electric current density range. Thus, the bright tin/copper alloy electroplating solution of the invention is suitable for industrial application.

Examples

[0018] The present invention will be described below in more detail by way of working examples, but it is to be understood that the invention is not limited thereto. Plating appearance in each of the following examples was evaluated by Hull cell test.

Example 1 & Comparative Examples 1~2

[0019] There was prepared a plating solution containing 30 g/L of tin methanesulfonate (as Sn^{2+}), 0.1 g/L of copper methanesulfonate (as Cu^{2+}), 200 g/L of methanesulfonic acid, 10 g/L of polyoxyethylene dodecyl ether, 1.5 g/L of dipropylene glycol methyl ether, 0.5 g/L of formaldehyde, 0.2 g/L of salicylaldehyde, 0.2 g/L of acetylacetone, 0.3 g/L of acrylic acid, and 0.7 g/L of catechol. Using this plating solution, plating was carried out at an electric current of 2A for 5 minutes, and the appearance of the resultant plating film was evaluated in a comparative manner. By way of comparison there was prepared a plating solution not containing a brightener. Then, using this comparative plating solution, Hull cell test was conducted under the same conditions as above. The results of evaluation based on Hull cell test are shown in Table 1. Examples 2~12 and Comparative Example 3

[0020] Plating solutions each comprising an aqueous solution and any of various dispersants and brighteners were prepared, the aqueous solution containing methanesulfonic acid and divalent tin salt and copper salt of the methanesulfonic acid as in Example 1. The plating solutions were then subjected to Hull cell test at an electric current of 2A for 5 minutes. For comparison, a plating solution containing neither brightener nor dispersant was prepared and then subjected to Hull cell test under the same conditions as above. The results of evaluation based on Hull cell test are shown in Table 1.

(Table 1)

Component (g/L)	Example												Comparative Example		
	1	2	3	4	5	6	7	8	9	10	11	12	1	2	3
Tin methanesulfonate (as Sn ²⁺)	30	30	30	30	30	30	30	30	30	30	30	30	30	30	30
Copper methanesulfonate (as Cu ²⁺)	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Methanesulfonic acid	200	200	200	200	200	200	200	200	200	200	200	200	200	200	200
Polyoxyethylene nonyl phenyl ether	-	10	-	10	-	10	-	10	-	10	-	10	-	10	-
Polyoxyethylene dodecyl ether	10	-	10	-	10	-	10	-	10	-	10	-	10	-	-
Propylene glycol methyl ether	-	-	1.5	1.5	-	-	1.5	1.5	-	-	1.5	1.5	-	-	-
Dipropylene glycol methyl ether	1.5	1.5	-	-	1.5	1.5	-	-	1.5	1.5	-	-	1.5	1.5	-
Formaldehyde	0.5	-	0.5	-	0.5	-	0.5	-	0.5	-	0.5	-	-	-	-
Propionaldehyde	-	0.5	-	0.5	-	0.5	-	0.5	-	0.5	-	0.5	-	-	-
Salicylaldehyde	0.2	-	0.2	-	0.2	-	0.2	-	0.2	-	0.2	-	-	-	-
1-Naphthaldehyde	-	0.2	-	0.2	-	0.2	-	0.2	-	0.2	-	0.2	-	-	-
Acetylacetone	0.2	-	0.2	-	0.2	-	0.2	-	0.2	-	0.2	-	-	-	-
Benzylidenacetone	-	0.2	-	0.2	-	0.2	-	0.2	-	0.2	-	0.2	-	-	-
Acrylic acid	0.3	0.3	0.3	0.3	-	-	-	-	0.3	0.3	0.3	0.3	-	-	-
Methacrylic acid	-	-	-	-	0.5	0.5	0.5	0.5	-	-	-	-	-	-	-
Catechol	0.7	0.7	0.7	0.7	0.7	0.7	0.7	0.7	-	-	-	-	0.7	0.7	0.7
Hydroquinone	-	-	-	-	-	-	-	-	0.7	0.7	0.7	0.7	-	-	-
Hull cell appearance	O	O	O	O	Δ	O	Δ	O	O	O	O	O	X	X	X
High current portion	O	O	O	O	O	O	O	O	O	O	O	O	X	X	X
Medium current portion	O	O	O	O	O	O	O	O	O	O	O	O	X	X	X
Low current portion	O	O	O	O	O	O	Δ	O	O	O	O	O	X	X	X


Hull cell appearance O : bright Δ : semi-bright X : mat

[0021] According to the present invention, as is apparent from the above results, there were obtained tin/copper alloy plating films having a bright or semi-bright smooth appearance over an area from high to low electric current portion. In contrast therewith, the comparative tin/copper alloy plating films were mat.

Claims

1. A cyanide-free bright tin/copper alloy electroplating solution which comprises an aqueous solution containing an organosulfonic acid, a divalent tin salt of the organosulfonic acid, a divalent copper salt of the organosulfonic acid, a dispersant, and a brightener.
2. A cyanide-free bright tin/copper alloy electroplating solution as set forth in claim 1, wherein said dispersant comprises at least two members selected from the group consisting of polyoxyethylene alkyl phenyl ethers, polyoxyethylene alkyl ethers, and alkylene glycol alkyl ethers.
3. A cyanide-free bright tin/copper alloy electroplating solution as set forth in claim 1, wherein said brightener comprises at least two members selected from the group consisting of aliphatic and aromatic aldehydes, aliphatic and aromatic ketones, and aliphatic carboxylic acids.
4. A cyanide-free bright tin/copper alloy electroplating solution, further containing an antioxidant.
5. A process for plating a tin/copper alloy upon a substrate, said process comprising:
 - a. contacting the substrate with a plating solution comprising:
 - (i) organosulfonic acid;
 - (ii) divalent tin salt of an organosulfonic acid;
 - (iii) divalent copper salt of an organosulfonic acid;
 - (iv) dispersant; and
 - (v) brightener; and
 - b. applying an electrical potential to the substrate thereby causing it to become a cathode and causing a tin/copper alloy to plate upon said substrate
6. A process according to claim 5, wherein said dispersant is selected from the group consisting of polyoxyethylene alkyl phenyl ethers, polyoxyethylene alkyl ethers, alkylene glycol alkyl ethers, and mixtures thereof.
7. A process according to claim 5 or 6, wherein said brightener comprises a material selected from the group consisting of aliphatic and aromatic aldehydes, aliphatic and aromatic ketones, aliphatic carboxylic acids and mixtures thereof.
8. A process according to claim 5, 6 or 7, wherein the plating solution also comprises an antioxidant.
9. A process according to claim 5, 6, 7 or 8, wherein said dispersant comprises at least two members selected from the group consisting of polyoxyethylene alkyl phenyl ethers, polyoxyethylene alkyl ethers, and alkylene glycol alkyl ethers.
10. A process according to claim 5, 6, 7, 8 or 9, wherein said brightener comprises at least two members selected from the group consisting of aliphatic and aromatic aldehydes, aliphatic and aromatic ketones, and aliphatic carboxylic acids.

This Page Blank (uspto)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 111 097 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:

05.02.2003 Bulletin 2003/06

(51) Int Cl.7: **C25D 3/60, C25D 3/58**

(43) Date of publication A2:

27.06.2001 Bulletin 2001/26

(21) Application number: **00309301.0**

(22) Date of filing: **23.10.2000**

(84) Designated Contracting States:

**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**

Designated Extension States:

AL LT LV MK RO SI

(30) Priority: **22.12.1999 JP 36540599**

(71) Applicant: **Nippon MacDermid Co., Ltd.**

Yokohama-Shi, Kanagawa-Ken 227 (JP)

(72) Inventor: **Tamura, Takaaki**

Kanagawa-ku, Yokohama, Kanagawa (JP)

(74) Representative: **Jenkins, Peter David et al**

PAGE WHITE & FARRER

54 Doughty Street

London WC1N 2LS (GB)

(54) **Bright tin-copper alloy electroplating solution**

(57) A tin/copper alloy electroplating solution capable of forming a bright plating film in a wide electric current density range is provided. The electroplating solution is a cyanide-free aqueous solution containing an or-

ganosulfonic acid, divalent tin and copper salts, as metal salts, of the organosulfonic acid, a dispersant, and a brightener.

EP 1 111 097 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 30 9301

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 4 347 107 A (TEICHMANN ROBERT J ET AL) 31 August 1982 (1982-08-31) * column 2, line 20-65; example III *	1-3,5-7	C25D3/60 C25D3/58
X	US 5 385 661 A (ANDRICACOS PANAYOTIS C ET AL) 31 January 1995 (1995-01-31) * column 5, line 29 - column 6, line 60 *	1,2,5	
X,P	EP 1 001 054 A (UYEMURA C & CO LTD) 17 May 2000 (2000-05-17) * page 4, line 51 - page 5, line 33; examples 6,7,26,27 *	1-10	
A	US 4 384 930 A (ECKLES WILLIAM E) 24 May 1983 (1983-05-24) * column 5, line 57,58 *	3,10	
A	US 5 948 235 A (ARAI SUSUMU) 7 September 1999 (1999-09-07) * column 3, line 51-53 *	8	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C25D
The present search report has been drawn up for all claims			
THE HAGUE		Date of completion of the search 17 December 2002	Examiner Van Leeuwen, R
<p>LIST OF CITED DOCUMENTS</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 30 9301

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

17-12-2002

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
US 4347107	A	31-08-1982	BE	892731 A1	01-10-1982
			BR	8201863 A	08-03-1983
			CA	1184872 A1	02-04-1985
			DE	3211329 A1	14-10-1982
			ES	8306194 A1	01-08-1983
			FR	2503192 A1	08-10-1982
			GB	2096175 A ,B	13-10-1982
			HK	67786 A	18-09-1986
			JP	57177987 A	01-11-1982
			NL	8201278 A	01-11-1982
			SE	8201736 A	03-10-1982
US 5385661	A	31-01-1995	NONE		
EP 1001054	A	17-05-2000	EP	1001054 A2	17-05-2000
			JP	2001026898 A	30-01-2001
			KR	2000035248 A	26-06-2000
			US	2002104763 A1	08-08-2002
US 4384930	A	24-05-1983	NONE		
US 5948235	A	07-09-1999	AU	1813397 A	22-09-1997
			DE	69713844 D1	14-08-2002
			EP	0829557 A1	18-03-1998
			JP	3335864 B2	21-10-2002
			JP	9296289 A	18-11-1997
			WO	9733015 A1	12-09-1997

EP 00 30 9301

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

This Page Blank (uspto)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☒ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

This Page Blank (uspto)